

CASING TECHNICAL DATA SHEET

4.5 x 0.29 P110 Long Round

Reviewed by: Sr. Quality Engineer Approved by: Corporate Director-QEHS

TDS Date (MM/DD/YY)

9/1/24

PIPE BODY DATA	Unit	Imperial	Metric
Nominal Outside Diameter	in	4.500	114.30
Nominal Wall Thickness	in	0.290	7.37
Remaining Body Wall (RBW)		95.0%	95.0%
Type of Thread		Long Round	Long Round
Grade		P110	P110
Label Weight		13.50	13.50
Plain End Weight	lb/ft	13.05	19.44
Pipe Minimum Yield	ksi	110	758
Pipe Maximum Yield	ksi	140	965
Pipe Minimum Tensile	ksi	125	862
Standard Drift Diameter (min)	in	3.795	96.38
Alternate Drift Diameter (min)	in	N/A	N/A
Pipe Body Plain End Yield	1b	422,000	191,420
Pipe Body Internal Yield	psi	13,470	92,870
Collapse Pressure - Standard	psi	10,690	73,700
Collapse Pressure - High	psi	N/A	N/A
CONNECTION DATA			
Coupling Minimum Yield	ksi	110	758
Coupling Maximum Yield	ksi	130	896
Coupling Minimum Tensile	ksi	125	862
Coupling or Joint Outside Diameter (nom)	in	5.250	133.35
Coupling Thread Fracture Strength	lb	819,000	371,490
Pipe Thread Fracture Strength	lb	338,000	153,310
Pull Out Strength	lb	366,000	166,010
Nominal Make-Up Torque or Make-up Torque Range	ft-lb	3,660	4,960
Coupling Internal Yield	psi	19,190	132,310
Internal Yield of Joint	psi	13,470	92,870
WELDED TUBE GENERAL INPUT CRITERIA			
Coupling Color Code		White	

Coupling Color Code
Coupling Color Code for the Band
Pipe Color Code Identification
Additional Color Band (approx.10' from box end)

	White
	None
2" Band(s)	One White
	N/A

Note:

Welded Tube has issued this document for general information only. This does not constitute a warranty, MTR, certificate of compliance, or similar. The content of this technical data sheet shall be reviewed by the user for verification of suitability and applicability. Anyone making use of this material does so at their own risk and assumes any and all liability resulting from such use. Welded Tube disclaims any and all expressed or implied warranties of fitness for particular application.

Welded Tube has the right to change this data at any time as an improvement of the product or process.

This is an un-controlled document.