

CASING TECHNICAL DATA SHEET

5.5 x 0.304 L80 Long Round

Reviewed by: Sr. Quality Engineer Approved by: Corporate Director-QEHS

TDS Date (MM/DD/YY)

9/1/24

1D3 Date (MM/DD/11) 9/1/24				
PIPE BODY DATA	Unit	Imperial	Metric	Unit
Nominal Outside Diameter	in	5.500	139.70	mm
Nominal Wall Thickness	in	0.304	7.72	mm
Remaining Body Wall (RBW)		95.0%	95.0%	1
Type of Thread		Long Round	Long Round	
Grade		L80	L80	1
Label Weight		17.00	17.00	1
Plain End Weight	lb/ft	16.89	25.13	kg/m
Pipe Minimum Yield	ksi	80	552	MPa
Pipe Maximum Yield	ksi	95	655	MPa
Pipe Minimum Tensile	ksi	95	655	MPa
Standard Drift Diameter (min)	in	4.767	121.08	mm
Alternate Drift Diameter (min)	in	N/A	N/A	mm
Pipe Body Plain End Yield	1b	397,000	180,080	kg
Pipe Body Internal Yield	psi	8,400	57,920	4
Collapse Pressure - Standard	psi	6,290	43,370	kPa
Collapse Pressure - High	psi	N/A	N/A	kPa
CONNECTION DATA	<u></u>			_
Coupling Minimum Yield	ksi	80	552	MPa
Coupling Maximum Yield	ksi	95	655	MPa
Coupling Minimum Tensile	ksi	95	655	MPa
Coupling or Joint Outside Diameter (nom)	in	6.300	160.02	mm
Coupling Thread Fracture Strength	1b	820,000	371,950	kg
Pipe Thread Fracture Strength	lb	338,000	153,310	kg
Pull Out Strength	lb	341,000	154,670	kg
Nominal Make-Up Torque or Make-up Torque Range	ft-lb	3,410	4,620	N-m
Coupling Internal Yield	psi	12,660	87,290	kPa
Internal Yield of Joint	psi	8,400	57,920	kPa
WELDED TUBE GENERAL INPUT CRITERIA				1
Coupling Color Code	Red			1
Coupling Color Code for the Band		One Brown		1

Coupling Color Code
Coupling Color Code for the Band
Pipe Color Code Identification
Additional Color Band (approx.10' from box end)

2	" Band(s))

	Red
	One Brown
1(s)	One Red, One Brown
	N/A

Note.

Welded Tube has issued this document for general information only. This does not constitute a warranty, MTR, certificate of compliance, or similar. The content of this technical data sheet shall be reviewed by the user for verification of suitability and applicability. Anyone making use of this material does so at their own risk and assumes any and all liability resulting from such use. Welded Tube disclaims any and all expressed or implied warranties of fitness for particular application.

Welded Tube has the right to change this data at any time as an improvement of the product or process.

This is an un-controlled document.