

## **CASING TECHNICAL DATA SHEET**

5.5 x 0.304 P110 Long Round

Reviewed by: Sr. Quality Engineer Approved by: Corporate Director-QEHS

TDS Date (MM/DD/YY)

9/1/24

PIPE BODY DATA	Unit	Imperial	Metric	Unit
Nominal Outside Diameter	in	5.500	139.70	mm
Nominal Wall Thickness	in	0.304	7.72	mm
Remaining Body Wall (RBW)		95.0%	95.0%	
Type of Thread		Long Round	Long Round	
Grade		P110	P110	]
Label Weight		17.00	17.00	1
Plain End Weight	lb/ft	16.89	25.13	kg/n
Pipe Minimum Yield	ksi	110		MPa
Pipe Maximum Yield	ksi	140	965	MPa
Pipe Minimum Tensile	ksi	125	862	MPa
Standard Drift Diameter (min)	in	4.767	121.08	mm
Alternate Drift Diameter (min)	in	N/A	N/A	mm
Pipe Body Plain End Yield	lb	546,000	247,660	kg
Pipe Body Internal Yield	psi	11,550	79,630	kPa
Collapse Pressure - Standard	psi	7,480	51,570	kPa
Collapse Pressure - High	psi	N/A	N/A	kPa
CONNECTION DATA				
Coupling Minimum Yield	ksi	110	758	MPa
Coupling Maximum Yield	ksi	130	896	MPa
Coupling Minimum Tensile	ksi	125	862	MPa
Coupling or Joint Outside Diameter (nom)	in	6.300	160.02	mm
Coupling Thread Fracture Strength	1b	1,079,000	489,430	kg
Pipe Thread Fracture Strength	1b	445,000	201,850	kg
Pull Out Strength	1b	462,000	209,560	kg
Nominal Make-Up Torque or Make-up Torque Range	ft-lb	4,620	6,260	N-m
Coupling Internal Yield	psi	17,410	120,040	kPa
Internal Yield of Joint	psi	11,550	79,630	kPa
WELDED TUBE GENERAL INPUT CRITERIA				,
Coupling Color Code		White		
Coupling Color Code for the Band		None		

Coupling Color Code
Coupling Color Code for the Band
Pipe Color Code Identification
Additional Color Band (approx.10' from box end)

	White
	None
2" Band(s)	One White
	N/A

Note:

Welded Tube has issued this document for general information only. This does not constitute a warranty, MTR, certificate of compliance, or similar. The content of this technical data sheet shall be reviewed by the user for verification of suitability and applicability. Anyone making use of this material does so at their own risk and assumes any and all liability resulting from such use. Welded Tube disclaims any and all expressed or implied warranties of fitness for particular application.

Welded Tube has the right to change this data at any time as an improvement of the product or process.

This is an un-controlled document.