

TDS Date (MM/DD/YY)

## CASING TECHNICAL DATA SHEET

7/8/24

5.5 x 0.415 EPL80 Plain End

Reviewed by: Sr. Quality Engineer Approved by: Corporate Director-QEHS

655 MPa

655 MPa

N/A mm

115.44 mm

246,750 kg

PIPE BODY DATA	Unit_	Imperial	Metric	Unit
Nominal Outside Diameter	in	5.500	139.70	mm
Nominal Wall Thickness	in	0.415	10.54	mm
Remaining Body Wall (RBW)		95.0%	95.0%	
Type of Thread		Plain End	Plain End	
Grade		EPL80	EPL80	
	-			-
Label Weight		23.00	23.00	
Plain End Weight	lb/ft	22.56	33.57	kg/m
Pipe Minimum Yield	ksi	82	565	MPa

ksi

ksi

in

in

lb

Pipe Minimum Yield Pipe Maximum Yield Pipe Minimum Tensile Standard Drift Diameter (min) Alternate Drift Diameter (min) Pipe Body Plain End Yield Pipe Body Internal Yield Collapse Pressure - Standard Collapse Pressure - High

## **CONNECTION DATA**

Coupling Minimum Yield

Coupling Maximum Yield Coupling Minimum Tensile Coupling or Joint Outside Diameter (nom) Coupling Thread Fracture Strength Pipe Thread Fracture Strength Pull Out Strength Nominal Make-Up Torque or Make-up Torque Range Coupling Internal Yield Internal Yield of Joint

## WELDED TUBE GENERAL INPUT CRITERIA

Coupling Color Code Coupling Color Code for the Band Pipe Color Code Identification Additional Color Band (approx.10' from box end)

psi	11,760	81,080	kPa
psi	11,440	78,880	kPa
psi	N/A	N/A	kPa
·			•
ksi	N/A	N/A	MPa
ksi	N/A	N/A	MPa
ksi	N/A	N/A	MPa
in	N/A	N/A	mm
1b	N/A	N/A	kg
1b	N/A	N/A	kg
1b	N/A	N/A	kg
ft-lb	N/A	N/A	N-m
psi	N/A	N/A	kPa
psi	N/A	N/A	kPa

95

95

4.545

544,000

N/A

	Red
	One Brown
2" Band(s)	One Red, One Brown
	White

## Note:

Welded Tube has issued this document for general information only. This does not constitute a warranty, MTR, certificate of compliance, or similar. The content of this technical data sheet shall be reviewed by the user for verification of suitability and applicability. Anyone making use of this material does so at their own risk and assumes any and all liability resulting from such use. Welded Tube disclaims any and all expressed or implied warranties of fitness for particular application.

Welded Tube has the right to change this data at any time as an improvement of the product or process.

This is an un-controlled document.