

CASING TECHNICAL DATA SHEET

5.5 x 0.415 HCL80 Long Round

Reviewed by: Sr. Quality Engineer Approved by: Corporate Director-QEHS

TDS Date (MM/DD/YY)

9/2/24

PIPE BODY DATA	Unit	Imperial	Metric
Nominal Outside Diameter	in	5.500	139.70
Nominal Wall Thickness	in	0.415	10.54
Remaining Body Wall (RBW)		95.0%	95.0%
Type of Thread		Long Round	Long Round
Grade		HCL80	HCL80
Label Weight		23.00	23.00
Plain End Weight	lb/ft	22.56	33.57
Pipe Minimum Yield	ksi	80	552
Pipe Maximum Yield	ksi	95	655
Pipe Minimum Tensile	ksi	95	655
Standard Drift Diameter (min)	in	4.545	115.44
Alternate Drift Diameter (min)	in	N/A	N/A
Pipe Body Plain End Yield	1b	530,000	240,400
Pipe Body Internal Yield	psi	11,470	79,080
Collapse Pressure - Standard	psi	N/A	N/A
Collapse Pressure - High	psi	11,530	79,500
CONNECTION DATA			
Coupling Minimum Yield	ksi	80	552
Coupling Maximum Yield	ksi	95	655
Coupling Minimum Tensile	ksi	95	655
Coupling or Joint Outside Diameter (nom)	in	6.300	160.02
Coupling Thread Fracture Strength	1b	820,000	371,950
Pipe Thread Fracture Strength	1b	489,000	221,810
Pull Out Strength	lb	493,000	223,620
Nominal Make-Up Torque or Make-up Torque Range	ft-lb	4,930	6,680
Coupling Internal Yield	psi	12,660	87,290
Internal Yield of Joint	psi	11,470	79,080
WELDED TUBE GENERAL INPUT CRITERIA			
Coupling Color Code		Red	

Coupling Color Code
Coupling Color Code for the Band
Pipe Color Code Identification
Additional Color Band (approx.10' from box end)

2" Band(s

	Red
	One Brown
(s)	One Red, One Brown
	Blue

Note:

Welded Tube has issued this document for general information only. This does not constitute a warranty, MTR, certificate of compliance, or similar. The content of this technical data sheet shall be reviewed by the user for verification of suitability and applicability. Anyone making use of this material does so at their own risk and assumes any and all liability resulting from such use. Welded Tube disclaims any and all expressed or implied warranties of fitness for particular application.

Welded Tube has the right to change this data at any time as an improvement of the product or process.

This is an un-controlled document.