



CASING TECHNICAL DATA SHEET
5.5 x 0.415 HPP110 GBCD

Reviewed by: Sr. Quality Engineer
 Approved by: Corporate Director-QEHS

TDS Date (MM/DD/YY)

6/26/24

PIPE BODY DATA

Nominal Outside Diameter
 Nominal Wall Thickness
 Remaining Body Wall (RBW)
 Type of Thread
 Grade

Label Weight
 Plain End Weight
 Pipe Minimum Yield
 Pipe Maximum Yield
 Pipe Minimum Tensile
 Standard Drift Diameter (min)
 Alternate Drift Diameter (min)
 Pipe Body Plain End Yield
 Pipe Body Internal Yield
 Collapse Pressure - Standard
 Collapse Pressure - High

Unit	Imperial	Metric	Unit
in	5.500	139.70	mm
in	0.415	10.54	mm
	95.0%	95.0%	
	GBCD	GBCD	
	HPP110	HPP110	
	23.00	23.00	
lb/ft	22.56	33.57	kg/m
ksi	125	862	MPa
ksi	140	965	MPa
ksi	125	862	MPa
in	4.545	115.44	mm
in	N/A	N/A	mm
lb	829,000	376,030	kg
psi	17,920	123,550	kPa
psi	N/A	N/A	kPa
psi	16,500	113,760	kPa

CONNECTION DATA

Coupling Minimum Yield
 Coupling Maximum Yield
 Coupling Minimum Tensile
 Coupling or Joint Outside Diameter (nom)
 Coupling Thread Fracture Strength
 Pipe Thread Fracture Strength
 Pull Out Strength
 Nominal Make-Up Torque or Make-up Torque Range
 Coupling Internal Yield
 Internal Yield of Joint

ksi	See Next Page	See Next Page	MPa
ksi	See Next Page	See Next Page	MPa
ksi	See Next Page	See Next Page	MPa
in	See Next Page	See Next Page	mm
lb	See Next Page	See Next Page	kg
lb	See Next Page	See Next Page	kg
lb	See Next Page	See Next Page	kg
ft-lb	See Next Page	See Next Page	N-m
psi	See Next Page	See Next Page	kPa
psi	See Next Page	See Next Page	kPa

WELED TUBE GENERAL INPUT CRITERIA

Coupling Color Code
 Coupling Color Code for the Band
 Pipe Color Code Identification
 Additional Color Band (approx.10' from box end)

2" Band(s)	White
	One Blue
	One White
	Orange

Note:

Welded Tube has issued this document for general information only. This does not constitute a warranty, MTR, certificate of compliance, or similar. The content of this technical data sheet shall be reviewed by the user for verification of suitability and applicability. Anyone making use of this material does so at their own risk and assumes any and all liability resulting from such use. Welded Tube disclaims any and all expressed or implied warranties of fitness for particular application.

Welded Tube has the right to change this data at any time as an improvement of the product or process.

This is an un-controlled document.

GB Connection Performance Properties Sheet

Rev. 0 (03/21/2024)

ENGINEERING THE RIGHT CONNECTIONS

Casing: 5.5 OD, 23 ppf
Casing Grade**: WTC HP P110 (95% RBW)

Connection: GB CD Butt 6.300
Coupling Grade: 125 ksi



PIPE BODY GEOMETRY					
Nominal OD (in.)	5 1/2	Wall Thickness (in.)	0.415	Drift Diameter (in.)	4.545
Nominal Weight (ppf)	23.00	Nominal ID (in.)	4.670	API Alternate Drift Dia. (in.)	N/A
Plain End Weight (ppf)	22.56	Plain End Area (in. ²)	6.630		

PIPE BODY PERFORMANCE**					
Material Specification	WTC HP P110 (95% RBW)	Min. Yield Str. (psi)	125,000	Min. Ultimate Str. (psi)	125,000
Collapse		Tension		Pressure	
API (psi)	16,060	Pl. End Yield Str. (kips)	829	Min. Int. Yield Press.** (psi)	17,920
High Collapse** (psi)	16,500	Torque		Bending	
		Yield Torque (ft-lbs)	94,350	Build Rate to Yield (°/100 ft)	104.2

GB CD Butt 6.300 COUPLING GEOMETRY			
Coupling OD (in.)	6.300	Makeup Loss (in.)	4.2500
Coupling Length (in.)	8.500	Critical Cross-Sect. (in. ²)	8.527

GB CD Butt 6.300 CONNECTION PERFORMANCE RATINGS/EFFICIENCIES					
Material Specification	125 ksi	Min. Yield Str. (psi)	125,000	Min. Ultimate Str. (psi)	135,000
Tension		Efficiency		Bending	
Thread Str. (kips)	779	Internal Pressure (%)	100%	Build Rate to Yield (°/100 ft)	90.9
Min. Tension Yield (kips)	1,013	External Pressure (%)	100%	Yield Torque	
Min. Tension Ult. (kips)	1,094	Tension (%)	100%	Yield Torque (ft-lbs)	43,350
Joint Str. (kips)	779	Compression (%)	100%		
		Ratio of Areas (Cplg/Pipe)	1.29		

MAKEUP TORQUE					
Min. MU Tq. (ft-lbs)	10,000	Max. MU Tq. (ft-lbs)	20,000	Running Tq. (ft-lbs)	See GBC RP
				Max. Operating Tq. (ft-lbs)*	41,180

Units: US Customary (lbm, in., °F, lbf)

1 kip = 1,000 lbs

* See Running Procedure for description and limitations.

See attached: Notes for GB Connection Performance Properties.

GBC Running Procedure (GBC RP): www.gbconnections.com/pdf/RP-GB-DWC-Connections.pdf

Blanking Dimensions: www.gbconnections.com/pdf/GB-DWC-Blanking-Dimensions.pdf

Connection yield torque rating based on physical testing or extrapolation therefrom

** Casing properties applicable to WTC HP P110 (95% RBW) grade with min. yield 125 ksi with 95% RBW.