

CASING TECHNICAL DATA SHEET

7 x 0.317 L80 Long Round

Reviewed by: Sr. Quality Engineer Approved by: Corporate Director-QEHS

TDS Date (MM/DD/YY)

9/2/24

1D3 Date (MM/DD/11) 9/2/24				
PIPE BODY DATA	Unit	Imperial	Metric	Unit
Nominal Outside Diameter	in	7.000	177.80	mm
Nominal Wall Thickness	in	0.317	8.05	mm
Remaining Body Wall (RBW)		95.0%	95.0%]
Type of Thread		Long Round	Long Round	
Grade		L80	L80]
Label Weight		23.00	23.00]
Plain End Weight	lb/ft	22.65	33.70	kg/m
Pipe Minimum Yield	ksi	80		MPa
Pipe Maximum Yield	ksi	95	655	MPa
Pipe Minimum Tensile	ksi	95	655	MPa
Standard Drift Diameter (min)	in	6.241	158.52	mm
Alternate Drift Diameter (min)	in	6.280	159.51	mm
Pipe Body Plain End Yield	1b	532,000	241,310	kg
Pipe Body Internal Yield	psi	6,880	47,440	kPa
Collapse Pressure - Standard	psi	3,830	26,410	kPa
Collapse Pressure - High	psi	N/A	N/A	kPa
CONNECTION DATA				
Coupling Minimum Yield	ksi	80	552	MPa
Coupling Maximum Yield	ksi	95	655	MPa
Coupling Minimum Tensile	ksi	95	655	MPa
Coupling or Joint Outside Diameter (nom)	in	7.875	200.03	mm
Coupling Thread Fracture Strength	1b	1,146,000	519,820	kg
Pipe Thread Fracture Strength	1b	461,000	209,110	kg
Pull Out Strength	1b	435,000	197,310	kg
Nominal Make-Up Torque or Make-up Torque Range	ft-lb	4,350	5,900	N-m
Coupling Internal Yield	psi	11,210	77,290	kPa
Internal Yield of Joint	psi	6,880	47,440	kPa
WELDED TUBE GENERAL INPUT CRITERIA				_
Coupling Color Code		Red		

Coupling Color Code
Coupling Color Code for the Band
Pipe Color Code Identification
Additional Color Band (approx.10' from box end)

2" Band(s)

	Red
	One Brown
(s)	One Red, One Brown
	N/A

Note:

Welded Tube has issued this document for general information only. This does not constitute a warranty, MTR, certificate of compliance, or similar. The content of this technical data sheet shall be reviewed by the user for verification of suitability and applicability. Anyone making use of this material does so at their own risk and assumes any and all liability resulting from such use. Welded Tube disclaims any and all expressed or implied warranties of fitness for particular application.

Welded Tube has the right to change this data at any time as an improvement of the product or process.

This is an un-controlled document.