

CASING TECHNICAL DATA SHEET

7 x 0.317 HCN80Q Plain End

Reviewed by: Sr. Quality Engineer Approved by: Corporate Director-QEHS

Blue

TDS Date (MM/DD/YY) 7/1/24

| PIPE BODY DATA | Unit | Imperial | Metric |
|--|------------|---------------------------|-----------|
| Nominal Outside Diameter | in | 7.000 | 177.80 |
| Nominal Wall Thickness | in | 0.317 | 8.05 |
| Remaining Body Wall (RBW) | | 95.0% | 95.0% |
| Type of Thread | | Plain End | Plain End |
| Grade | | HCN80Q | HCN80Q |
| Label Weight | | 23.00 | 23.00 |
| Plain End Weight | lb/ft | 22.65 | 33.70 |
| Pipe Minimum Yield | ksi | 80 | 552 |
| Pipe Maximum Yield | ksi | 110 | 758 |
| Pipe Minimum Tensile | ksi | 100 | 689 |
| Standard Drift Diameter (min) | in | 6.241 | 158.52 |
| Alternate Drift Diameter (min) | in | 6.280 | 159.51 |
| Pipe Body Plain End Yield | lb | 532,000 | 241,310 |
| ipe Body Internal Yield | psi | 6,880 | 47,440 |
| Collapse Pressure - Standard | psi | N/A | N/A |
| Collapse Pressure - High | psi | 4,970 | 34,270 |
| CONNECTION DATA | | | |
| Coupling Minimum Yield | ksi | N/A | N/A |
| Coupling Maximum Yield | ksi | N/A | N/A |
| Coupling Minimum Tensile | ksi | N/A | N/A |
| oupling or Joint Outside Diameter (nom) | in | N/A | N/A |
| Coupling Thread Fracture Strength | lb | N/A | N/A |
| ripe Thread Fracture Strength | lb | N/A | N/A |
| Pull Out Strength | lb | N/A | N/A |
| Iominal Make-Up Torque or Make-up Torque Range | ft-lb | N/A | N/A |
| Coupling Internal Yield | psi | N/A | N/A |
| nternal Yield of Joint | psi | N/A | N/A |
| VELDED TUBE GENERAL INPUT CRITERIA | | | |
| Coupling Color Code | | Red | |
| Coupling Color Code for the Band | | Green | |
| Pipe Color Code Identification | 2" Band(s) | One Red, One Bright Green | |
| 11111 101 5 1/ 1016 1 1) | | D1 | |

Note:

Additional Color Band (approx.10' from box end)

Welded Tube has issued this document for general information only. This does not constitute a warranty, MTR, certificate of compliance, or similar. The content of this technical data sheet shall be reviewed by the user for verification of suitability and applicability. Anyone making use of this material does so at their own risk and assumes any and all liability resulting from such use. Welded Tube disclaims any and all expressed or implied warranties of fitness for particular application.

Welded Tube has the right to change this data at any time as an improvement of the product or process.

This is an un-controlled document.