Welded Tube Fueling Growth, Shaping Futures

CASING TECHNICAL DATA SHEET 8.625 x 0.304 HCL80 Long Round

Reviewed by: Sr. Quality Engineer Approved by: Corporate Director-QEHS

	0/2/24		
PIPE BODY DATA	Unit	Imperial	Metric
Nominal Outside Diameter	in	8.625	219.08
Nominal Wall Thickness	in	0.304	7.72
Remaining Body Wall (RBW)		95.0%	95.0%
Type of Thread		Long Round	Long Round
Grade		HCL80	HCL80
Label Weight		28.00	28.00
Plain End Weight	lb/ft	27.04	40.24
Pipe Minimum Yield	ksi	80	552
Pipe Maximum Yield	ksi	95	655
Pipe Minimum Tensile	ksi	95	655
Standard Drift Diameter (min)	in	7.892	200.46
Alternate Drift Diameter (min)	in	7.972	202.49
Pipe Body Plain End Yield	lb	636,000	288,480
Pipe Body Internal Yield	psi	5,360	36,960
Collapse Pressure - Standard	psi	N/A	N/A
Collapse Pressure - High	psi	2,630	18,130
CONNECTION DATA			
Coupling Minimum Yield	ksi	80	552
Coupling Maximum Yield	ksi	95	655
Coupling Minimum Tensile	ksi	95	655
Coupling or Joint Outside Diameter (nom)	in	9.625	244.48
Coupling Thread Fracture Strength	lb	1,611,000	730,740
Pipe Thread Fracture Strength	lb	544,000	246,750
Pull Out Strength	lb	486,000	220,450
Nominal Make-Up Torque or Make-up Torque Range	e ft-lb	4,860	6,590
Coupling Internal Yield	psi	10,500	72,390
Internal Yield of Joint	psi	5,360	36,960
WELDED TUBE GENERAL INPUT CRITERIA			
Coupling Color Code		Red	
Coupling Color Code for the Band		One Brown	
Pipe Color Code Identification	2" Band(s)	One Red. One Brown	

Pipe Color Code Identification Additional Color Band (approx.10' from box end)

	Red	
	One Brown	
2" Band(s)	One Red, One Brown	
	Blue	

Note:

Welded Tube has issued this document for general information only. This does not constitute a warranty, MTR, certificate of compliance, or similar. The content of this technical data sheet shall be reviewed by the user for verification of suitability and applicability. Anyone making use of this material does so at their own risk and assumes any and all liability resulting from such use. Welded Tube disclaims any and all expressed or implied warranties of fitness for particular application.

Welded Tube has the right to change this data at any time as an improvement of the product or process.

This is an un-controlled document.