## Welded Tube

Fueling Growth, Shaping Futures

## CASING TECHNICAL DATA SHEET 8.625 x 0.304 J55 Long Round

Reviewed by: Sr. Quality Engineer Approved by: Corporate Director-QEHS

N/A

TDS Date (MM/DD/YY)	9/2/24				
PIPE BODY DATA		Unit	Imperial	Metric	
Nominal Outside Diameter		in	8.625	219.08	
Nominal Wall Thickness		in	0.304	7.72	
Remaining Body Wall (RBW)			95.0%	95.0%	
Type of Thread			Long Round	Long Round	
Grade			J55	J55	
Label Weight			28.00	28.00	
Plain End Weight		lb/ft	27.04	40.24	
Pipe Minimum Yield		ksi	55	379	
Pipe Maximum Yield		ksi	80	552	
Pipe Minimum Tensile		ksi	75	517	
Standard Drift Diameter (min)		in	7.892	200.46	
Alternate Drift Diameter (min)		in	7.972	202.49	
Pipe Body Plain End Yield		lb	437,000	198,220	
Pipe Body Internal Yield		psi	3,680	25,370	
Collapse Pressure - Standard		psi	1,880	12,960	
Collapse Pressure - High		psi	N/A	N/A	
CONNECTION DATA					
Coupling Minimum Yield		ksi	55	379	
Coupling Maximum Yield		ksi	80	552	
Coupling Minimum Tensile		ksi	75	517	
Coupling or Joint Outside Diameter (nom)		in	9.625	244.48	
Coupling Thread Fracture Strength		lb	1,272,000	576,970	
Pipe Thread Fracture Strength		lb	430,000	195,040	
Pull Out Strength		lb	348,000	157,850	
Nominal Make-Up Torque or Make-up Torque	Range	ft-lb	3,480	4,720	
Coupling Internal Yield		psi	7,220	49,780	
nternal Yield of Joint		psi	3,680	25,370	
WELDED TUBE GENERAL INPUT CRITERIA					
Coupling Color Code			Bright Green		
Coupling Color Code for the Band			One White		
Pipe Color Code Identification		2" Band(s)	One Bright (	One Bright Green	
			DT / A		

Additional Color Band (approx.10' from box end)

Note:

Welded Tube has issued this document for general information only. This does not constitute a warranty, MTR, certificate of compliance, or similar. The content of this technical data sheet shall be reviewed by the user for verification of suitability and applicability. Anyone making use of this material does so at their own risk and assumes any and all liability resulting from such use. Welded Tube disclaims any and all expressed or implied warranties of fitness for particular application.

Welded Tube has the right to change this data at any time as an improvement of the product or process.

This is an un-controlled document.