

TDS Date (MM/DD/YY)

Coupling Minimum Tensile

Coupling or Joint Outside Diameter (nom)

Coupling Thread Fracture Strength

Pipe Thread Fracture Strength

Pull Out Strength

Coupling Internal Yield

CASING TECHNICAL DATA SHEET

 $9.625 \times 0.352 \text{ J}55 \text{ Plain End}$

7/1/24

Reviewed by: Sr. Quality Engineer Approved by: Corporate Director-QEHS

N/A MPa

N/A mm

N/A kg

N/A kg

N/A kg

N/A N-m

N/A kPa

N/A kPa

PIPE BODY DATA	Unit	Imperial	Metric	Unit
Nominal Outside Diameter	in	9.625	244.48	mm
Nominal Wall Thickness	in	0.352	8.94	mm
Remaining Body Wall (RBW)		95.0%	95.0%	
Type of Thread		Plain End	Plain End	
Grade		J55	J55]
Label Weight		36.00	36.00]
Plain End Weight	lb/ft	34.89	51.93	kg/m
Pipe Minimum Yield	ksi	55	379	MPa
Pipe Maximum Yield	ksi	80	552	MPa
Pipe Minimum Tensile	ksi	75	517	MPa
Standard Drift Diameter (min)	in	8.765	222.63	mm
Alternate Drift Diameter (min)	in	N/A	N/A	mm
Pipe Body Plain End Yield	lb	564,000	255,830	kg
Pipe Body Internal Yield	psi	3,820	26,340	kPa
Collapse Pressure - Standard	psi	2,020	13,930	kPa
Collapse Pressure - High	psi	N/A	N/A	kPa
CONNECTION DATA				_
Coupling Minimum Yield	ksi	N/A	N/A	MPa
Coupling Maximum Yield	ksi	N/A	N/A	MPa

Internal Yield of Joint	
WELDED TUBE GENERAL INPUT CRITERIA	

Nominal Make-Up Torque or Make-up Torque Range

Coupling Color Code
Coupling Color Code for the Band
Pipe Color Code Identification
Additional Color Band (approx.10' from box end)

2" Band(s)

ksi

in

1b

1b

1b

ft-lb

psi

psi

_	
	Bright Green
	One White
(s)	One Bright Green
	N/A

N/A

N/A

N/A

N/A

N/A

N/A

N/A

N/A

Note:

Welded Tube has issued this document for general information only. This does not constitute a warranty, MTR, certificate of compliance, or similar. The content of this technical data sheet shall be reviewed by the user for verification of suitability and applicability. Anyone making use of this material does so at their own risk and assumes any and all liability resulting from such use. Welded Tube disclaims any and all expressed or implied warranties of fitness for particular application.

Welded Tube has the right to change this data at any time as an improvement of the product or process.

This is an un-controlled document.