

CASING TECHNICAL DATA SHEET

9.625 x 0.472 HCP110 Buttress

Reviewed by: Sr. Quality Engineer Approved by: Corporate Director-QEHS

Blue

TDS Date (MM/DD/YY)

9/2/24

PIPE BODY DATA	Unit	Imperial	Metric	Unit	
Nominal Outside Diameter	in	9.625	244.48	mm	
Nominal Wall Thickness	in	0.472	11.99	mm	
Remaining Body Wall (RBW)		95.0%	95.0%		
Type of Thread		Buttress	Buttress		
Grade		HCP110	HCP110		
Label Weight		47.00	47.00	1	
Plain End Weight	lb/ft	46.18	68.75	kg/m	
Pipe Minimum Yield	ksi	110	758	MPa	
Pipe Maximum Yield	ksi	140		MPa	
Pipe Minimum Tensile	ksi	125	862	MPa	
Standard Drift Diameter (min)	in	8.525	216.53	mm	
Alternate Drift Diameter (min)	in	N/A	·	mm	
Pipe Body Plain End Yield	lb	1,493,000	677,210		
Pipe Body Internal Yield	psi	10,250	70,670	-	
Collapse Pressure - Standard	psi	N/A	N/A	kPa	
Collapse Pressure - High	psi	6,660	45,920	kPa	
CONNECTION DATA				_	
Coupling Minimum Yield	ksi	110	758	MPa	
Coupling Maximum Yield	ksi	130	896	MPa	
Coupling Minimum Tensile	ksi	125	862	MPa	
Coupling or Joint Outside Diameter (nom)	in	10.625	269.88	mm	
Coupling Thread Fracture Strength	lb	2,197,000	996,540		
Pipe Thread Fracture Strength	lb	1,500,000	680,390		
Pull Out Strength	lb	N/A	N/A		
Nominal Make-Up Torque or Make-up Torque Range	ft-lb	N/A	N/A	N-m	
Coupling Internal Yield	psi	12,150	83,770	4	
Internal Yield of Joint	psi	10,250	70,670	kPa	
WELDED TUBE GENERAL INPUT CRITERIA				_	
Coupling Color Code		White			
Coupling Color Code for the Band		None			
Pipe Color Code Identification	2" Band(s)	One Wh	One White		

Note:

Additional Color Band (approx.10' from box end)

Welded Tube has issued this document for general information only. This does not constitute a warranty, MTR, certificate of compliance, or similar. The content of this technical data sheet shall be reviewed by the user for verification of suitability and applicability. Anyone making use of this material does so at their own risk and assumes any and all liability resulting from such use. Welded Tube disclaims any and all expressed or implied warranties of fitness for particular application.

Welded Tube has the right to change this data at any time as an improvement of the product or process.

This is an un-controlled document.